



Rezkem Office Plaza
56 Milford Drive, Suite 100
Hudson Ohio 44236
330-653-9104

Current Issue Date:
June, 2017
Version Number 3

Product Data Sheet

Alphatac™ 95R Hydrocarbon Resin

Alphatac 95R is a hydrocarbon resin used for rubber applications as well as road marking paint, adhesives, and other applications requiring C5 hydrocarbon resin. It is yellow in color and comes in a granular form. In paint applications, Alphatac 95R enhances the hardness and adhesive force of the paint material, while forming a smooth-coated surface, all while making the paint waterproof, UV resistant, and resistant to chemical erosion.

Physical Properties

Specifications

Softening Point, R&B°
(ASTM E-28)

95 – 105

Color Gardner (50% resin solids in toluene)
(ASTM D-1544)

Max 5 – Typical 5

Melt Viscosity @ 200°C
(ASTM D-3236)

≤ 250

Acid Value (mg KOH/g)
(ASTM D-974)

≤ 8

Form: Granular
Package: 25kg bags, super sacks, bulk

Due to chemical structure and composition, granulated and flaked resins may be subject to clumping, blocking and/or fusing. The previously mentioned matters can be accelerated if materials are subjected to any or all of the following conditions: 1) storage of material is prolonged; 2) material is above the ambient temperature; 3) material is exposed to pressure, i.e. stacking pallets, or a compounding of the previously listed conditions.

In order to preserve the composition of the material, it is recommended to: 1) avoid prolonged storage of the material; 2) store the material in a temperature-controlled area; 3) use caution when stacking or applying pressure to the material.

Note: clumping, blocking, and/or fusing does not have negative effects on the material specifications.

We believe the information contained in this document is reliable. However, this does not release our customers from the obligation to test the products supplied by us as to their suitability for intended process and end use. Since many of the applications, uses, and processing of the products are beyond our control, we cannot be held liable for any consequential service failures that occur.