



Rezkem Office Plaza
56 Milford Drive, Suite 100
Hudson Ohio 44236
330-653-9104

Current Issue Date:
June, 2017
Version Number 3

Product Data Sheet

Arotac™ 130L Hydrocarbon Resin

Arotac 130L is an aromatic, thermoplastic resin with low molecular weight. It is produced from petroleum derived C9 fraction through a thermal-polymerization technique. It ranges from light yellow to yellow in color and comes in the form of transparent granular solids. Arotac 130L provides good water resistance, heat stability, and compatability with synthetic rubber, resins, and polymers. The Arotac line of products is recommended for use in: coatings, paints, contact adhesives, hot melt adhesives, rubber, and inks.

Physical Properties

Specifications

Softening Point, R&B°
(ASTM E-28)

125 – 135

Color Gardner (50% resin solids in toluene)
(ASTM D-1544)

Max 6 – Typical 3

Bromine Value (Br.g/100g)
(ASTM D-1159)

≤ 35

Specific Gravity @ 25°C
(ASTM D-1475)

1.05 - 1.10

Acid Value (mgKOH/g)
(ASTM D-974)

≤ 0.3

Ash Content %
(ASTM D-1063)

≤ 0.05

Form: Granular

Package: 25kg bags, super sacks, bulk

Due to chemical structure and composition, granulated and flaked resins may be subject to clumping, blocking and/or fusing. The previously mentioned matters can be accelerated if materials are subjected to any or all of the following conditions: 1) storage of material is prolonged; 2) material is above the ambient temperature; 3) material is exposed to pressure, i.e. stacking pallets, or a compounding of the previously listed conditions.

In order to preserve the composition of the material, it is recommended to: 1) avoid prolonged storage of the material; 2) store the material in a temperature-controlled area; 3) use caution when stacking or applying pressure to the material.

Note: clumping, blocking, and/or fusing does not have negative effects on the material specifications.

We believe the information contained in this document is reliable. However, this does not release our customers from the obligation to test the products supplied by us as to their suitability for intended process and end use. Since many of the applications, uses, and processing of the products are beyond our control, we cannot be held liable for any consequential service failures that occur.